



Initial permeability	μ_i	25°C	4000±25%
Saturation magnetic flux density	B_s (mT)	25°C	430
Remanent flux density	B_r (mT)	100°C	270
Remanent flux	B_r (mT)	25°C	80

