



**Bs-Temperature**




Initial permeability	$\mu_i$	25°C	3200±25%
Saturation magnetic flux density	Bs(mT)	25°C	530
		100°C	420
Remanence	Br(mT)	25°C	130
		100°C	80
Coercivity	Hc(A/m)	25°C	11
		100°C	10
		25°C	350

Temperature	25°C	100°C	200°C
Resistivity	$\rho(\Omega\cdot m)$	3	
Density	d(kg/m <sup>3</sup> )	4.8×10 <sup>5</sup>	
Toroid(mm)			
	25		
	15		
	7.5		

**$\mu_i$ -Temperature**



**B-H**



**$\mu_i$ -Frequency**

