


Bs-Temperature

H=1194A/m




Initial permeability	μ_i	25°C	3000±25%
Saturation magnetic flux density	Bs(mT)	25°C	530
Remanence	Br(mT)	25°C	100
Core loss	Pcv(kW/m³)	60°C	320
		120°C	320
		140°C	380
Electrical resistivity	$\rho(\Omega\cdot m)$		4
Density	d(kg/m³)		4.9×10³

li-Temperature


Test core : Toroid(mm)

OD : 25

ID : 15



μ_i -Frequency



B-H

